

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 097 968 A1**

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
09.05.2001 Bulletin 2001/19

(51) Int Cl.⁷: **C08L 83/12, C08L 83/14,
A61K 7/48, C08J 3/03**

(21) Application number: **00122754.5**

(22) Date of filing: **19.10.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

- **Schulz, William James Jr.**
Midland, Michigan 48640 (US)
- **Smith, Janet Mary**
Bay City, Michigan 48706 (US)

(30) Priority: **08.11.1999 US 435044**

(71) Applicant: **DOW CORNING CORPORATION**
Midland Michigan 48686-0994 (US)

(74) Representative:
Sternagel, Fleischer, Godemeyer & Partner
Patentanwälte
Braunsberger Feld 29
51429 Bergisch Gladbach (DE)

(72) Inventors:
• **Lin, Zuchen**
Midland, Michigan 48640 (US)

(54) **Mixtures of silicone elastomers**

(57) A blend of (i) a crosslinked elastomeric silicone polyether and (ii) a crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms is dis-

closed. The new composition can be used in preparing water-in-oil emulsions, and clear solutions containing an oil(s) or an oil-soluble active ingredient(s).

EP 1 097 968 A1

Description

- [0001] This invention provides a blend of silicone elastomers which can be used to compatibilize organic oils. The blend can also be used to prepare water-in-organic oil emulsions. The organic oils can be as polar as sunflower oil known to have an interfacial tension of 19.3 mN/m. These benefits cannot be achieved using only one of the silicone elastomers.
- [0002] For example, it was determined that Vitamin A was not soluble in either one of the silicone elastomers, but that it could be solubilized in a blend of the two silicone elastomers. This provides an improved delivery system for active ingredients such as Vitamin A, which are generally considered to be difficult to solubilize.
- [0003] If desired, emulsions containing a blend of the silicone elastomers can be used for delivering water soluble active ingredients such as Vitamin C and α -hydroxy acids. In addition, it has been demonstrated that certain linear silicone polyethers can be used in place of one of the silicone elastomers in forming these new blends.
- [0004] A crosslinked elastomeric silicone polyether is disclosed in U.S. Patent 5,811,487. A crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms is disclosed in U.S. Patent 5,880,210.
- [0005] However, neither of these patents describe as a new composition of matter, a blend of (i) a crosslinked elastomeric silicone polyether, and (ii) a crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms.
- [0006] The patents also fail to suggest either a water-in-oil emulsion containing the new composition of matter, or a clear solution containing the new composition of matter.
- [0007] The patents further fail to suggest as a second new composition of matter, a blend of (i) a linear silicone polyether, and (ii) the crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms. In addition, the patents fail to suggest a water-in-oil emulsion containing the second new composition of matter.
- [0008] These new and novel concepts are the subject matter of the present invention.
- [0009] Or invention provides a new composition of matter which is a blend of (i) a crosslinked elastomeric silicone polyether, and (ii) a crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms.
- [0010] The invention also relates to a water-in-oil emulsion containing this composition of matter. In addition, the invention relates to a clear solution containing the composition.
- [0011] In an alternate embodiment of the invention, a second new composition of matter is provided, which is a blend of (i) a linear silicone polyether, and (ii) the crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms.
- [0012] According to this alternate embodiment, a water-in-oil emulsion can also be formed containing the second new composition of matter.
- [0013] One composition of matter according to the present invention is a blend of (i) a crosslinked elastomeric silicone polyether, and (ii) a crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms.
- [0014] The crosslinked elastomeric silicone polyether and methods of preparing crosslinked elastomeric silicone polyethers are described in detail in US Patent 5,811,487.
- [0015] Generally, such crosslinked elastomeric silicone polyethers are prepared by reacting an $\equiv\text{Si-H}$ containing polysiloxane (A) and a mono-alkenyl polyether (B) in the presence of a platinum catalyst, until an $\equiv\text{Si-H}$ containing siloxane with polyether groups (C) is formed. The $\equiv\text{Si-H}$ containing siloxane with polyether groups (C) is then reacted with an unsaturated hydrocarbon (D) such as an alpha, omega-diene, in the presence of a solvent (E) and a platinum catalyst, until a silicone elastomer is formed by crosslinking and addition of $\equiv\text{SiH}$ across double bonds in the alpha, omega-diene (D).
- [0016] The crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms and methods of preparing crosslinked elastomeric silicones containing alkyl groups having 3-40 carbon atoms are described in detail in U.S. Patent 5,880,210.
- [0017] Generally, such crosslinked elastomeric silicones containing alkyl groups having 3-40 carbon atoms are prepared by reacting an $\equiv\text{Si-H}$ containing polysiloxane (A), an alpha-olefin (B), and an alpha, omega-diene (C). The reaction is conducted in the presence of a platinum catalyst, and in the presence of a low molecular weight silicone oil or other solvent (D). The reaction is carried out by grafting long chain alkyl groups from the alpha-olefin (B) onto the $\equiv\text{Si-H}$ containing polysiloxane (A), and then crosslinking and addition of $\equiv\text{Si-H}$ in the grafted $\equiv\text{Si-H}$ containing polysiloxane across double bonds in the alpha, omega-diene (C).
- [0018] While the crosslinked elastomeric silicone containing alkyl groups may contain alkyl groups having 3-40 carbon atoms, preferably, the crosslinked elastomeric silicone containing alkyl groups should contain alkyl groups having 16-30 carbon atoms.
- [0019] In preparing blends according to the present invention, the crosslinked elastomeric silicone polyether and the crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms are mixed, i.e., blended, in a weight ratio of from 4:1 to 1:8, preferably 1:1 to 1:4.
- [0020] Both the crosslinked elastomeric silicone polyether and the crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms constitute polymeric molecules which are crosslinked together to form a gel consisting

of a three-dimensional molecular polymeric network containing tens, hundreds, and thousands of crosslinking units between and among the polymeric molecules. Typically, they each contain and are swollen with from 65 to 98 percent by weight of an oil.

[0021] Both U.S. Patent 5,811,487 and US Patent 5,880,210 contain extensive lists of appropriate oils which can be used, among which are volatile polydimethylsiloxanes such as octamethyltrisiloxane and decamethylcyclopentasiloxane, nonvolatile polydimethylsiloxanes, aliphatic hydrocarbons such as pentane and heptane, aromatic hydrocarbons such as benzene and toluene, alcohols such as methanol and ethanol, aldehydes such as formaldehyde, ketones such as acetone and methyl ethyl ketone, amines such as methylamine, esters such as ethyl acetate, ethers such as tetrahydrofuran, glycols such as glycerol, glycol ethers such as ethylene glycol monomethylether, alkyl halides such as chloroform and carbon tetrachloride, aromatic halides such as chlorobenzene, flavoring agents such as peppermint oil and fragrances such as musk and myrrh.

[0022] One particularly suitable use of the mixture of the crosslinked elastomeric silicone polyether and the crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon, is for the preparation of water-in-oil emulsions consisting of an aqueous disperse phase and an oil continuous phase. In that application, the aqueous phase may contain a water soluble active ingredient, and the oil phase may contain an oil or an oil soluble active ingredient.

[0023] The water soluble active ingredient for the aqueous phase of the water-in-oil emulsion can be, for example, (i) a water soluble Vitamin, (ii) a water soluble drug, or (ii) an α -hydroxy acid such as glycolic acid, lactic acid, tartaric acid and citric acid, i.e., fruit acids. In this latter instance, significant benefits can be realized as fruit acids have been alleged to be capable of diminishing fine skin lines and pigmentation spots, as well as stimulating collagen which allows the skin to repair itself.

[0024] U.S. Patent 5,948,855 contains an extensive list of some appropriate water soluble Vitamins and water soluble drugs which can be used, among which are Vitamin C, Vitamin B₁, Vitamin B₂, Vitamin B₆, Vitamin B₁₂, niacin, folic acid, biotin and pantothenic acid. The water-soluble vitamin can be used in the water-in-oil emulsion in amounts of from 0.01 to 50 percent by weight.


[0025] The oil for the oil phase of the water-in-oil emulsion is most preferably an organic oil, generally, a natural oil that is derived from an animal, a vegetable, or a mineral source. Modern cosmetic oils are most representative of the organic oil, and among the more common organic oils known to be safe for cosmetic purposes are almond oil, apricot kernel oil, avocado oil, cacao butter (theobroma oil), carrot seed oil, castor oil, citrus seed oil, coconut oil, corn-oil, cottonseed oil, cucumber oil, egg oil, jojoba oil, lanolin oil, linseed oil, mineral oil, mink oil, olive oil, palm kernel oil, peach kernel oil, peanut oil, rapeseed oil, safflower oil, sesame oil, shark liver oil, soybean oil, sunflower seed oil, sweet almond oil, tallow (beef) oil, tallow (mutton) oil, turtle oil, vegetable oil, whale oil and wheat germ oil.

[0026] U.S. Patent 5,948,855 also contains an extensive list of some appropriate oil soluble active ingredients such as vitamins and drugs which can be used in the oil phase of the water-in-oil emulsion, among which are vitamins, including but not limited to, Vitamin A₁, RETINOL, C₂-C₁₈ esters of RETINOL, Vitamin E, TOCOPHEROL, esters of Vitamin E and mixtures thereof. RETINOL includes trans-RETINOL, 13-cis-RETINOL, 11-cis-RETINOL, 9-cis-RETINOL, and 3,4-didehydro-RETINOL. Other vitamins which are appropriate include RETINYL ACETATE, RETINYL PALMITATE, RETINYL PROPIONATE, α -TOCOPHEROL, TOCOPHERSOLAN, TOCOPHERYL ACETATE, TOCOPHERYL LINOATE, TOCOPHERYL NICOTINATE and TOCOPHERYL SUCCINATE. The oil-soluble vitamin or drug can be used in the water-in-oil emulsion in amounts of from 0.01 to 50 percent by weight.

[0027] In preparing water-in-oil emulsions according to the present invention, the aqueous phase comprises 0.1 to 99 percent by weight of the emulsion, including the weight of any water-soluble active ingredient. The oil phase comprises 1 to 99.9 percent by weight of the emulsion, including the weight of the crosslinked elastomeric silicone polyether, the weight of the crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms, and the weight of the oil or oil-soluble active ingredient. Preferably, the aqueous phase comprises 20 to 95 percent by weight of the emulsion, and the oil phase comprises 5 to 80 percent by weight of the emulsion.

[0028] When clear solutions are desired rather than emulsions, the crosslinked elastomeric silicone polyether, the crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms, and the oil or oil-soluble active ingredient, are used in generally the same proportions as noted above. Clear solutions can be obtained by hand shaking the ingredients rather than by mixing them mechanically.

[0029] In some instances, it may be desirable to use a silicone polyether that is not a crosslinked elastomer. In a second embodiment of the present invention, therefore, a linear silicone polyether can be substituted for the crosslinked elastomeric silicone polyether. One such linear silicone polyether has a structure corresponding to the formula:



[0030] In the formula, R^a is an alkyl group of one to six carbon atoms; R^b is the radical $-\text{C}_m\text{H}_{2m}-$; R^c is a terminating radical such as hydrogen, an alkyl group of one to six carbon atoms, or an aryl group such as phenyl. m has a value of two to eight. p and s each have a value such that the oxyalkylene segment $-(\text{C}_2\text{H}_4\text{O})_p-(\text{C}_3\text{H}_6\text{O})_s-$ has a molecular weight in the range of 400 to 5,000. The oxyalkylene segment preferably contains 50-99 mole percent of oxyethylene units $-(\text{C}_2\text{H}_4\text{O})_p-$, and 1-50 mole percent of oxypropylene units $-(\text{C}_3\text{H}_6\text{O})_s-$. x has a value of 10 to 500. y has a value of 2 to 100.

[0031] Preferably, R^a and terminating radical R^c are both methyl groups. m is preferably three or four. The group R^b is most preferably the $-(\text{CH}_2)_3-$ group. The values of p and s are such as to provide a molecular weight of the oxyalkylene segment $-(\text{C}_2\text{H}_4\text{O})_p-(\text{C}_3\text{H}_6\text{O})_s-$ of between 1,000 to 3,000. Most preferably, p should be 4 to 60, and s should be 0 to 60. These types of linear silicone polyethers are generally known in the art, and are commercially available from global sources such as the Dow Corning Corporation, Midland, Michigan, USA.

[0032] The following examples are set forth in order to illustrate this invention in more detail.

Example 1 - Water-in-Oil Emulsion (W/O) Containing Sunflower Oil

[0033] 10.0 gram of a crosslinked elastomeric silicone polyether prepared according to methods described in U.S. Patent 5,811,487, in which 20 percent of the repeating units in its backbone contained units that included the moiety $-(\text{CH}_2\text{CH}_2\text{O})_n-$ in which n had a value of 12, were weighed into a blender cup. To the blender cup were added 10.0 gram of a crosslinked elastomeric silicone containing alkyl groups having 16 carbon atoms prepared according to methods described in U.S. Patent 5,880,210. These two ingredients were blended together using a mechanical mixer set at medium speed for 30 seconds. 10.0 gram of this mixture were weighed into a glass beaker along with 20.0 gram of sunflower oil and the contents of the beaker were mixed using a mechanical mixer set at a speed of 600 rpm (63 rad/s). After 5 minutes of mixing, 70.0 gram of deionized water were added to the beaker over a 15 minute period using a peristaltic pump. The product obtained was a water-in-oil emulsion which had the consistency of a white cream.

Example 2 - W/O Emulsion Containing Sunflower Oil & Mineral Oil

[0034] 5.02 gram of the crosslinked elastomeric silicone polyether used in Example 1 were weighed into a glass beaker, along with 5.03 gram of the crosslinked elastomeric silicone containing alkyl groups having 16 carbon atoms used in Example 1, 10.21 gram of sunflower oil, and 10.04 gram of mineral oil. The four ingredients were mixed together using a mechanical mixer at 600 rpm (63 rad/s). After 5 minutes of mixing, 76.78 gram of deionized water were added to the beaker over a 15 minute period while mixing at 800 rpm (84 rad/s). The mixing speed was increased to 1,000 rpm (105 rad/s) after the addition of water and continued for another 15 minutes. The product obtained was a water-in-oil emulsion which had the consistency of a white cream.

Example 3 - W/O Emulsion Containing Sunflower Oil

[0035] 10.0 gram of the crosslinked elastomeric silicone polyether used in Example 1 were weighed into a glass beaker, along with 20.2 gram of a crosslinked elastomeric silicone containing alkyl groups having 18 carbon atoms, and 10.30 gram of sunflower oil. The three ingredients were mixed together using a mechanical mixer at 600 rpm (63 rad/s). After 5 minutes of mixing, 10.1 gram of deionized water were added to the beaker over a 15 minute period. The product obtained was a water-in-oil emulsion which had the consistency of a white cream.

Example 4 - W/O Emulsion Containing Sunflower Oil

[0036] 13.3 gram of the crosslinked elastomeric silicone containing alkyl groups having 16 carbon atoms used in Example 1 were weighed into a blender cup, along with 6.7 gram of a linear silicone polyether instead of a crosslinked elastomeric silicone polyether. The linear silicone polyether had a viscosity of 1,700 centistoke (mm^2/s), and a structure generally corresponding to the formula shown previously, in which all of the R^a groups were methyl and where p and s each had a value of 18. These two ingredients were blended together at a medium setting using a mechanical mixer

for 30 seconds. The two silicone emulsifiers and 15.0 gram of sunflower oil were mixed together using the mechanical mixer at 600 rpm (63 rad/s). After 5 minutes of mixing, 15.0 grams of deionized water were added to the beaker over a 15 minute period using a peristaltic pump. Upon completion of the addition of water, the ingredients were mixed for an additional 5 minutes. The product obtained was a water-in-oil emulsion which had the consistency of a white cream.

Example 5 - Clear Solution Containing Vitamin A Palmitate

[0037] 7.97 gram of the crosslinked elastomeric silicone polyether used in Example 1 and 2.22 gram of Vitamin A Palmitate, i.e., Retinyl Palmitate, were weighed into a glass beaker. Mixing these two ingredients by hand shake resulted in forming a turbid mixture in the beaker. 2.00 grams of the turbid mixture were weighed into another glass beaker, along with 2.00 grams of the crosslinked elastomeric silicone containing alkyl groups having 18 carbon atoms used in Example 3. The beaker contents were mixed together by simply hand shaking the beaker. This resulted in forming a clear solution in the beaker.

[0038] While the blends, the emulsions and the clear solutions described herein are useful in applications requiring any benefit attributed to organosilicon materials, these blends, emulsions and clear solutions are primarily intended for use in personal care. Thus, they can be used alone or combined with cosmetic ingredients to form a number of over-the-counter (OTC) personal care products. For example, they are useful as carriers in antiperspirants and deodorants. They are lubricious and can improve the properties of skin creams, skin care lotions, moisturizers, facial treatments such as acne or wrinkle removers, personal and facial cleansers, bath oils, perfumes, colognes, sachets, sunscreens, pre-shave and after-shave lotions, liquid soaps, shaving soaps and shaving lathers. They can be used in hair shampoos, hair conditioners, hair sprays, mousses, permanents, depilatories and cuticle coats, to enhance gloss and provide conditioning benefits.


[0039] In cosmetics, they can function as leveling and spreading agents for pigments in make-ups, color cosmetics, foundations, blushes, lipsticks, lip balms, eyeliners, mascaras, oil removers, color cosmetic removers and powders. When incorporated into sticks, gels, lotions, aerosols and roll-ons, they can impart a dry and silky-smooth feel.

[0040] These blends, emulsions and clear solutions are also capable of functioning as carriers for pharmaceuticals, biocides, herbicides, pesticides and other biologically active substances; and they have utility as additives for cellulosic or synthetic nonwoven carrier substrates used in wet-like cleansing wipes such as wet-wipes, tissues and towels, marketed generally for personal hygiene and household cleaning tasks.

[0041] While elastomeric silicones prepared according to U.S. Patents 5,811,487 and 5,880,210, are most preferred for use according to this invention, other types of elastomeric silicones may be employed herein without departing from the spirit of the invention, provided they are similar in performance and benefits to the preferred elastomeric silicones. For example, they can be prepared by using other kinds of organosilicon monomers as set forth in detail in U.S. Patent 5,948,855. They can also be prepared by the one pot method as outlined in U.S. Patent 5,889,108.

Claims

1. A composition of matter comprising a blend of (i) a crosslinked elastomeric silicone polyether, and (ii) a crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms, the crosslinked elastomeric silicone polyether and the crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms being present in the blend in a weight ratio of 4:1 to 1:8.
2. A composition according to claim 1 in which the crosslinked elastomeric silicone (i) and the crosslinked elastomeric silicone (ii) contain and are swollen with from 65 to 98 percent by weight of an oil.
3. A composition of matter comprising a blend of (i) a linear silicone polyether, and (ii) a crosslinked elastomeric silicone containing alkyl groups having 3-40 carbon atoms, the linear silicone polyether (i) and the crosslinked elastomeric silicone (ii) being present in the blend in a weight ratio of 4:1 to 1:8.
4. A composition according to claim 3 in which the linear silicone polyether (i) has the formula:



where R^a is an alkyl group of one to six carbon atoms; R^b is the radical - C_mH_{2m}-; R^c is a terminating radical selected from the group consisting of hydrogen, an alkyl group of one to six carbon atoms, or an aryl group; m has a value of two to eight; p and s have values such that the oxyalkylene segment -(C₂H₄O)_p-(C₃H₆O)_s- has a molecular weight in the range of 400 to 5,000; the segment having 50-99 mole percent of oxyethylene units -(C₂H₄O)_p- and 1-50 mole percent of oxypropylene units -(C₃H₆O)_s-; x has a value of 10 to 500; and y has a value of 2 to 100.

5. A composition according to claim 3 in which the crosslinked elastomeric silicone (ii) contains and is swollen with from 65 to 98 percent by weight of an oil.
6. A water-in-oil emulsion comprising an aqueous disperse phase and an oil continuous phase, the oil phase containing the composition defined in claims 1 or 3.
7. A water-in-oil emulsion according to claims 1 or 6 in which one or both of the aqueous phase contains a water soluble active ingredient, or the oil phase contains an oil or an oil soluble active ingredient.
8. A product containing the composition of matter according to claim 1 the product being selected from the group consisting of antiperspirants, deodorants, skin creams, skin care lotions, moisturizers, acne removers, wrinkle removers, facial cleansers, bath oils, perfumes, colognes, sachets, sunscreens, pre-shave lotions, after-shave lotions, liquid soaps, shaving soaps, shaving lathers, hair shampoos, hair conditioners, hair sprays, mousses, permanents, depilatories, cuticle coats, make-up, color cosmetics, foundations, blushes, lipsticks, lip balms, eye-liners, mascara, oil removers, color cosmetic removers, pharmaceuticals, biocides, herbicides, pesticides, wet-wipes and tissue wipes.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 12 2754

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A,D	US 5 811 487 A (SCHULZ JR WILLIAM JAMES ET AL) 22 September 1998 (1998-09-22) * abstract * * column 2, line 1 - column 6, line 24; claims; examples * ---	1-8	C08L83/12 C08L83/14 A61K7/48 C08J3/03
A,D	US 5 880 210 A (SCHULZ JR WILLIAM JAMES ET AL) 9 March 1999 (1999-03-09) * column 2, line 22 - column 6, line 65; claims; examples * ---	1-8	
P,A	EP 1 010 715 A (GEN ELECTRIC) 21 June 2000 (2000-06-21) * paragraph '0039!; examples 9-12,14 * -----	1-8	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08L A61K C08J
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 15 January 2001	Examiner Hutton, D
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P04C01)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 00 12 2754

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-01-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5811487 A	22-09-1998	CN 1185314 A	24-06-1998
		EP 0848029 A	17-06-1998
		JP 10176059 A	30-06-1998
US 5880210 A	09-03-1999	EP 0869142 A	07-10-1998
EP 1010715 A	21-06-2000	JP 2000198851 A	18-07-2000

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82